



**GENERAL
STRUCTURES
INC**
A DWM COMPANY

WWW.GENERALSTRUCTURESINC.COM

Field Painting Procedure

The entire surface area of the pole that needs to be touched up should be scuff-sanded with a 320-grit, non-silicone sandpaper.

The surface should then be washed with an industrial solvent and wiped clean with a lint-free painter's rag or tack cloth.

The finish coat should be an exterior quality air-dried acrylic enamel, or other paint that is compatible with TGIC polyester powder, to match fixture.

If using touch-up spray to match a textured finish, it is recommended to hold the spray can approximately 12"-14" away from the surface area (a slightly longer distance than traditional applications). Spray the paint using a sweeping back-and-forth and up-and-down motion for best results.